



PT. SUMBER WISESA INDOLESTARI **INDUSTRIAL COATING & CHEMICALS**

Head Office : Jl. Raya Mauk KM. 7 kawasan Industry Karet Jaya Blok Karet Jaya II No. 7 Sepatan – Tangerang
Telp. : (021) 59372418 (Hunting) Fax. : (021) 59372384, E-mail : swi_paint@telkom.net

MELAMINE GLOSS TOP COATING

DESCRIPTION :

SWI MELAMINE TOP COATING is two component, high gloss, high solid acid curing lacquer.

CHARACTERICTIC :

SWI MELAMINE TOP COATING is fast drying, shortly coating time, hard film coating, good adhesion, oil resistance, water resistance, solvent resistance, weak acid basic resistance, it gives double result in coating film.

APPLICATION :

SWI MELAMINE TOP COATING is suitable for using as finishing coat for wood items, made of solid wood, plywood, rattan and chipboard etc. It is recommended for indoor use.

SPECIFICATION :

Type	: Two component acid curing top coating
Hardener	: SWI Melamine Hardener
Thinner	: SWI Melamine Thinner
Mixing ratio	: Melamine Top Coating : Hardener 10 : 1 (by volume)
Solid content by weight	: 61,5%
Appearance	: Transparent



PT. SUMBER WISESA INDOLESTARI **INDUSTRIAL COATING & CHEMICALS**

Head Office : Jl. Raya Mauk KM. 7 kawasan Industry Karet Jaya Blok Karet Jaya II No. 7 Sepatan – Tangerang
Telp. : (021) 59372418 (Hunting) Fax. : (021) 59372384, E-mail : swi_paint@telkom.net

Dry to touch	: 10 Minutes
Hard Dry	: 3 - 4 Hours
Pot life a 25°C	: 1 Day
Spraying viscosity a 25°C	: 12" – 17" NK2
Specific gravity	: 1,03 gr/cc